




Single Course Face Bricks - 76mm

| Technical Information |  |  |  |
|--|---|--|---|
| | CREAMS | REDS | TANS/GREYS |
| Length x Width x Height (mm) | 230 x 70 x 76 | 230 x 70 x 76 | 230 x 70 x 76 |
| Pack dimensions (mm) | 920 x 700 x 912 | 920 x 700 x 912 | 920 x 700 x 912 |
| Dimensional category | DW1 | DW1 | DW1 |
| No per pack | 432 | 432 | 432 |
| Approximate number per m ² (including mortar joint) | 48.5 | 48.5 | 48.5 |
| Approximate unit weight (kg) | 1.7 | 1.82 | 1.7 |
| Approximate pack weight (kg) | 734 | 786 | 734 |
| Coring orientation | Vertical | Vertical | Vertical |
| Characteristic unconfined compressive strength f_{uc} (MPa) | > 12 | > 15 | > 15 |
| 24 hour cold water absorption (%) | < 15 | < 12 | < 12 |
| Nominal wall surface density (kg/m ²) | 113 | 117 | 113 |
| Dry bulk density (kg/m ³) | 1,400 | 1,485 | 1,400 |
| Co-efficient of expansion $-e_m$ (mm/m/15yrs) | < 1.0 | < 1.0 | < 1.0 |
| Perforation volume (%) | < 30 | < 30 | < 30 |
| Gross initial rate of absorption (kg/m ² /min) | < 2.2 | < 1.8 | < 1.8 |
| Salt attack resistance category | Exposure | Exposure | Exposure |
| Liability to efflorescence | Nil to Slight | Nil to Slight | Nil to Slight |
| Lime pitting | Nil | Nil | Nil |
| Solar absorbance rating | Medium | Medium | Medium |



CLAYBRICK Face Brick

Single Course Face Bricks - 76mm



The product technical information supplied is only for product manufactured by Brikmakers Pty Ltd. Brikmakers product is distributed by The Brick Shop.

Product meets the minimum tolerance levels stipulated in Australian/New Zealand Standards AS/NZS 4455. Testing is carried out in accordance with Australian/New Zealand Standards AS/NZS 4456 test methods where applicable. Durability classification is based on product knowledge under Perth, Western Australia climatic conditions.

This technical information represents average properties obtained from production lots and is for general **description** purposes only. If specific test results are required, this must be clarified and agreed prior to shipping so samples can be taken from the relevant production lot.

Information is subject to change without notice. All colours are indicative only.

Please confirm all technical, colour and installation specifications are applicable to your application.

brikmakers.com info@brikmakers.com
